

# E410BO – Technical Datasheet

## 1. Chemical & Mechanical Properties

Property	Value
C	≤ 0.22%
Mn	≤ 1.50%
P	≤ 0.045%
S	≤ 0.040%
Si	≤ 0.45%
Cu	-
Yield Strength (YS)	≥ 410 MPa
Tensile Strength (TS)	550 – 700 MPa
Elongation	≥ 17%
Hardness	180 – 210 HB
Impact Test	27J min at 0°C (Charpy V-Notch)

## 2. Equivalent / Alternative Grades

Standard	Grade	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation / Impact
IS 2062	E410BO	≤ 0.22	≤ 1.50	≤ 0.045	≤ 0.040	≤ 0.45	-	≥ 410	550 – 700	≥ 17% / 27J @ 0°C
EN 10025-2	S420JR	≤ 0.22	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	-	≥ 420	490 – 630	≥ 22% / 27J @ 20°C
ASTM A572	Gr 50	≤ 0.26	≤ 1.35	≤ 0.040	≤ 0.050	≤ 0.40	-	≥ 345	450 – 620	≥ 21% / 20J @ RT

## 3. Common Applications

- Structural steel
- Construction and fabrication
- Machinery parts

- Bridges
- Automotive industry

#### 4. Standard Conformance

IS 2062:2011 – Indian Standard for Hot Rolled Medium and High Tensile Structural Steel.

Grade Code Meaning:

E: Killed steel; 410: Minimum yield strength in MPa; BO: Thermo-mechanically rolled grade

#### 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents