

# S600MC — EN 10149-2 (2013) - Technical Data sheet

---

## 1. Chemical & Mechanical Properties

C (%)	Mn (%)	Si (%)	P (%)	S (%)	Yield (MPa)	UTS (MPa)	Elong (%)
0.12	1.90	0.50	0.025	0.015	≥600	650–820	11 / 13

## 2. Equivalent / Alternative Grades

Grade	Standard	YS	UTS	C max (%)
Strenx 700MC	SSAB	700	950	0.12
ASTM A1018 HSLAS-F Grade 70	ASTM A1018	485	595	0.20

## 3. Common Applications

- Heavy crane booms
- Bridge sections
- High-strength machine frames

## 4. Standard Conformance

EN 10149-2 : 2013 — High-strength, thermomechanically rolled steels for cold forming

## 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.