

45C8 – IS 2507 : 1975– Technical Datasheet

1. Chemical & Mechanical Properties

Property	Value / Range
C (%)	0.40–0.48
Mn (%)	0.60–0.90
Si (%)	0.10–0.35
S max (%)	0.050
P max (%)	0.050
Tensile Strength (MPa)	850 – 1 000
Yield Strength (MPa)	≥ 700
Hardness (HB)	250 – 302
Elongation (%)	10

2. Equivalent / Alternative Grades

Grade	Standard	C %	Mn %	Key Alloy	S % max	P % max	Typical σ_u / HB
SAE 1045	ASTM A29	0.43–0.50	0.60–0.90	Si ≤ 0.35	0.040	0.040	σ_u 565 – 725 (normalized); HB 170 – 217
JIS S45C	JIS G 4051	0.42–0.48	0.60–0.90	Si ≤ 0.35	0.040	0.040	σ_u 570 – 700; HB 180 – 220
EN C45E (1.1191)	EN 10083-2	0.42–0.50	0.50–0.80	Si ≤ 0.40	0.025	0.025	σ_u 560 – 780 (QT); HB 170 – 230

3. Common Applications

- Leaf & coil springs under moderate stress
- Clutch springs, small flat springs

4. Standard Conformance

Cold-rolled spring-steel strip conforming to IS 2507 : 1975.

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents