

# 80C6 – IS 2507: 1975– Technical Datasheet

# 1. Chemical & Mechanical Properties

Property	Value / Range		
C (%)	0.75-0.85		
Mn (%)	0.60-0.90		
Si (%)	0.10-0.35		
S max (%)	0.050		
P max (%)	0.050		
Tensile Strength (MPa)	1 300 – 1 500		
Yield Strength (MPa)	≥ 1 100		
Hardness (HB)	340 - 420		
Elongation (%)	5		

#### 2. Equivalent / Alternative Grades

Grade	Standard	С%	Mn %	Key Alloy	S % max	P % max	Typical σu / HB
SAE 1080	ASTM A29	0.75-0.88	0.60–0.90	Si ≤ 0.35	0.040	0.040	σu 900 – 1100; HB 260 – 322
JIS SK80	JIS G 4401	0.75-0.84	0.60-0.90	Si ≤ 0.35	0.030	0.030	σu 890 – 1090; HB 260 – 322
EN C80S (1.2235)	EN 10132-4	0.78-0.88	0.50-0.90	Si 0.10– 0.35	0.025	0.025	σu 900 – 1150 (+LC); HB 260 – 330

### **3. Common Applications**

- Leaf & coil springs under severe service
- Hand tools, knives

#### 4. Standard Conformance

Cold-rolled spring-steel strip conforming to IS 2507 : 1975.

# 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.