

85C6 – IS 2507: 1975– Technical Datasheet

1. Chemical & Mechanical Properties

Property	Value / Range
C (%)	0.80–0.90
Mn (%)	0.60–0.90
Si (%)	0.10–0.35
S max (%)	0.050
P max (%)	0.050
Tensile Strength (MPa)	1 350 – 1 550
Yield Strength (MPa)	≥ 1 150
Hardness (HB)	350 – 430
Elongation (%)	5

2. Equivalent / Alternative Grades

Grade	Standard	C %	Mn %	Key Alloy	S % max	P % max	Typical σ_u / HB
SAE 1085	ASTM A29	0.80–0.93	0.60–0.90	Si ≤ 0.35	0.040	0.040	σ_u 940 – 1140; HB 270 – 335
JIS SK85	JIS G 4401	0.80–0.89	0.60–0.90	Si ≤ 0.35	0.030	0.030	σ_u 930 – 1130; HB 270 – 335
EN C85W2 (1.1269)	EN 10132-4	0.80–0.90	0.50–0.90	Si 0.10–0.35	0.025	0.025	σ_u 950 – 1180 (+LC); HB 275 – 345

3. Common Applications

- High-energy springs
- Handsaw & blades

4. Standard Conformance

Cold-rolled spring-steel strip conforming to IS 2507 : 1975.

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.