

# ISC1300M – IS 513 Part 2 (2016) – Martensitic- Technical Datasheet

## 1. Chemical & Mechanical Properties

Property	Value
C (%)	≤0.25
Mn (%)	≤2.00
Si (%)	≤0.50
P (%)	≤0.020
S (%)	≤0.020
Al (%)	0.02–0.06
Ti (%)	≤0.15
Nb (%)	≤0.09
Yield Strength YS (MPa min)	1300
Tensile Strength UTS (MPa min)	1400
Elongation A80 (%) min	10

## 2. Equivalent / Alternative Grades

Grade	Standard	C%	Mn %	Si%	P%	S%	Al%	Ti%	Nb %	UTS (MPa)	YS (MPa)
EN Gr 1300	EN 10338	≤0.25	≤2.00	≤0.50	≤0.020	≤0.020	0.02 – 0.06	≤0.15	≤0.09	1400	1300
ASTM Gr 1300	ASTM A1008	≤0.25	≤2.00	≤0.50	≤0.020	≤0.020	0.02 – 0.06	≤0.15	≤0.09	1420	1300
JFS Gr 1300	JFS A2001	≤0.25	≤2.00	≤0.50	≤0.020	≤0.020	0.02 – 0.06	≤0.15	≤0.09	1430	1300

## 3. Common Applications

- Crash-relevant structural parts
- Strength/weight optimised panels

## 4. Standard Conformance

Cold-reduced sheet/strip conforming to IS 513 Part 2 (2016).

## 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for general reference only. While we endeavour to ensure that the information is as accurate and up-to-date as possible, no warranty, express or implied, is given as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. accepts no liability for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For authoritative and legally binding specifications, users must refer to the official publications of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents