

310S – IS 6911: 2017 – Technical Datasheet

1. Chemical & Mechanical Properties (Annealed, CR)

| Property | Value | |
|-------------------|-----------|--|
| C (%) | ≤0.08 | |
| Mn (%) | ≤2.00 | |
| Si (%) | ≤1.50 | |
| P (%) | ≤0.045 | |
| S (%) | ≤0.030 | |
| Cr (%) | 24.0-26.0 | |
| Ni (%) | 19.0-22.0 | |
| Mo (%) | _ | |
| N (%) | _ | |
| UTS (MPa min) | 515 | |
| YS 0.2% (MPa min) | 205 | |
| El (%) min | 40 | |

2. Equivalent / Alternative Grades

| Grade | Standard | UNS | EN | JIS |
|-------|---|--------|--------|---------|
| 310S | ASTM A240 / EN 10088 / JIS G 4305 | S31008 | 1.4845 | SUS310S |

3. Common Applications

- High-temperature service
- Heat exchangers
- Chemical processing

4. Standard Conformance

Cold-rolled stainless-steel sheet/strip conforming to IS 6911: 2017.

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and upto-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.