

BSK 46 – High-Strength Formable Quality Hot-Rolled Steel

1. Chemical & Mechanical Properties

Property	Value / Range
C (%)	≤ 0.12
Mn (%)	≤ 1.40
Si (%)	≤ 0.40
P (%)	≤ 0.025
S (%)	≤ 0.025
Nb + Ti + V (%)	≤ 0.05
Yield Strength YS (MPa min)	450
Tensile Strength UTS (MPa)	500 - 640
Elongation A80 (%) min	21

2. Equivalent / Alternative Grades

Grade	Standard	С%	Mn%	Si%	Р%	S%	Nb/V/Ti	YS (MPa)	UTS (MPa)	El (%)
S460MC	EN 10149-2	≤0.12	≤1.60	≤0.50	≤0.025	≤0.015	≤0.09	460	520-670	14
HSLAS-F Gr 65	ASTM A1011	≤0.23	≤1.35	—	≤0.040	≤0.040	≥0.005 ea	450	≥550	18
SAPH 440	JIS G 3113	≤0.12	≤1.60	≤0.03	≤0.040	≤0.040		305	≥440	29-35

3. Common Applications

- Wheel-rim discs and flanges
- Automotive chassis members and cross-members
- Roll-formed tubes, poles, and crash structures
- High-strength structural profiles with high hole-expansion requirements

4. Standard / Supply Note

BSK 46 is a proprietary Indian HSLA grade developed for wheel-rim and chassis applications. It is ordered as hot-rolled or HRPO coil/plate to the mill's BSK 46 specification with cross-reference to IS 5986 or IS 10748 for general requirements (tolerances, testing).

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.