

# ASTM A516 Grade 65 – Technical Datasheet

## 1. Chemical & Mechanical Properties

Element / Property	Value
C	≤ 0.28%
Mn	≤ 1.40%
P	≤ 0.040%
S	≤ 0.040%
Si	≤ 0.50%
Cu	-
YS	≥ 260 MPa
TS	485 – 620 MPa
Elongation	≥ 21%
Impact	27J min at -29°C
Hardness	N/A

## 2. Equivalent / Alternative Grades

Standard	Grade	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	YS (MPa)	TS (MPa)	Elongation / Impact
IS 2062	E400C / E400CCu	≤ 0.22	≤ 1.55	≤ 0.045	≤ 0.040	≤ 0.45	0.15 – 0.25	≥ 400	460 – 590	≥ 20% / 27J @ -10°C
EN 10025-2	S355J2	≤ 0.22	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	≥ 0.20	≥ 355	470 – 630	≥ 22% / 27J @ -10°C
ASTM A572	Gr 50	≤ 0.23	≤ 1.35	≤ 0.040	≤ 0.050	≤ 0.40	≥ 0.20	≥ 345	450 – 620	≥ 21% / 20J @ RT

## 3. Common Applications

- Higher strength pressure vessels

- Heavy engineering applications

#### 4. Standard Conformance

ASTM A516 Specification for Pressure Vessel Plates, Carbon Steel, for Moderate- and Lower-Temperature Service.

Grade Code Meaning:

Grade number indicates minimum yield strength in ksi (e.g. 65 = 65 ksi = 448 MPa)

#### 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.